

SOPRAXPS 300 WI EN

Description

SOPRAXPS 300 WI EN is a rigid thermal insulation board made of extruded polystyrene (XPS) foam produced according to climate-friendly CO₂ technology.

SOPRAXPS 300 WI EN is mainly used as thermal insulation including underground constructions, supporting beams and formwork. The waffled surface of the board allows direct interior plastering.

Packing & Storage

Thickness (mm)	Boards/ pack	m ² /pack	Boards/pallet ⁽¹⁾	m ² /pallet ⁽¹⁾	Thermal resistance (R ₀) (m ² .K/W) ⁽²⁾
40	10	7,5	120	90,0	1,25
50	8	6,0	96	72,0	1,55
60	7	5,3	84	63,0	1,85
80	5	3,8	60	45,0	2,50
100	4	3,0	48	36,0	3,10
120	3	2,3	42	31,5	3,75
140	3	2,3	36	27,0	4,35
160	2	1,5	32	24,0	5,00
180	2	1,5	28	21,0	5,60
200	2	1,5	24	18,0	6,25
220	2	1,5	20	15,0	6,85
240	2	1,5	20	15,0	7,50
260	1	0,8	18	13,5	7,85
280	1	0,8	16	12,0	8,45

(1) In addition to the default pallet, there is also a "jumbo" pack, composed of 2x2 pallets.

Store the insulation boards on a flat surface, keep dry, protected from sunlight and temperatures above 75 °C.

Characteristics

Thermal conductivity - λ _D (W/(m.K)) (EN 12667)	40 ≤ d ≤ 240 mm 240 < d ≤ 280 mm	0,032 ⁽²⁾ 0,033 ⁽²⁾
Length (mm) (EN 822)		1250 ± 8
Width (mm) (EN 822)		600 ± 8
Thickness tolerance - d _N (EN 823)		T1
Density (kg/m ³)		34 ± 15 %
Edge profile		straight
Surface		waffled
Compressive strength at 10 % deformation (kPa) (EN 826)		CS(10\Y)300
Dimensional stability (≤ 5 %) (EN 1604)		DS(70,90)
Long term water absorption by total immersion (%) (EN 12087)		WL(T)0,7
Reaction to fire (EN 13501-1)		E
Water vapour diffusion resistance - μ (EN ISO 10456)		150
Tensile strength perpendicular to faces (kPa) (EN 1607)	40 ≤ d < 80 mm 80 ≤ d ≤ 280 mm	NPD TR200
Durability of compressive creep against ageing/degradation (kPa) (EN 1606)		NPD

NPD = no performance determined

(2) The variation due to aging of the thermal conductivity and resistance has been taken into account in the indicated performance

Installation

Use a suitable adhesive for adhesion to underground walls.

Always consult the local regulations and contact the manufacturer for technical questions.

Immediately after installation the insulation boards must be protected against weather conditions, sunlight and temperatures above 75 °C.

Special indications

Hygiene, Health and Environment

The product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

Quality-, Environment- and Safety Management

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.

